



GNP Graystar

Specialty Materials

TECHNICAL DATA SHEET

Boron Nitride Powder (BN)

Typical Chemistry

	HBN-1	HBN-2	HBN-3
Boron Nitride (BN)	≥ 98 %	≥ 99 %	≥ 99.3 %
Boron Trioxide (B ₂ O ₃)	≤ 1.3 %	≤ 0.5 %	≤ 0.2 %
Oxygen (C)	≤ 1.5 %	≤ 0.8 %	≤ 0.5 %
Carbon (C)	≤ 0.5 %	≤ 0.3 %	≤ 0.2 %

Typical Properties

	HBN-1	HBN-2	HBN-3
d50 (µm)	1.5-2.0	1.5-2.0	1.5-2.0
SSA (m ² /g)	10-20	10-20	10-20
Tap Density (g/cm ³)	0.2-0.4	0.2-0.4	0.2-0.4

Description:

GNP Graystar's Boron Nitride has a hexagonal crystal structure, allowing for a loose, lightweight lubricative powder that can easily absorb moisture. Hexagonal Boron Nitride (HBN) shows high thermal conductivity, as well as excellent corrosion resistance and chemical inertness.

Applications:

GNP Graystar's Boron Nitride powder is used primarily in electronic thermal management applications and as a lubricant. It is also used in ceramic manufacturing, automotive and aerospace applications, thermal sprays, cosmetics, and more.

info@GNPGraystar.com

Rev. 02/2020

Northern Office

37 John Glenn Dr.
Amherst, NY 14228
716.759.6600

www.GNPGraystar.com

Southern Office

9 Simmonsville Rd.
Bluffton, SC 29910
843.815.5600