





| Aluminum Oxide (Al ₂ O ₃) | 99.78 % |
|--|---------|
| Silicon Dioxide (SiO ₂) | 0.04 % |
| Sodium Dioxide (Na ₂ O) | 0.10 % |
| Iron Oxide (Fe ₂ O ₃) | 0.09 % |

Physical Characteristics

| Crystal Form | Alpha - Alumina |
|---------------|------------------------|
| True Density | 3.95 g/cm ³ |
| Melting Point | 2000°C |
| Color | White |
| Hardness | Mohs: 9.0 |

Test Methods

| Sizing: | FEPA F Standard 42-2:2006 FEPA P Standard 43-2:2006 JIS B 6001-1987 |
|---------|---|
| | Custom Sizes Available |
| | |



Description:

GNPGraystar's White Aluminum Oxide is electrically fused in an arc furnce using Bayer process high purity alumina. The final product is used in applications where higher purity levels and lower iron content is desired as compared to brown aluminum oxide.

Applications:

GNPGraystar's White Aluminum Oxide powders are used for precision lapping, micro blasting, fine grit bond and coated applications, thermal coatings, polishing compounds, and more.

info@GNPGraystar.com

Rev. 02/2020