



# GNP Graystar

Specialty Materials

AN ISO 9001 CERTIFIED COMPANY



## TECHNICAL DATA SHEET

### Fused Zirconia Mullite

#### Typical Chemistry

	Typical	Guaranteed
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> )	46.0 %	44.5 - 47.0 %
Silicon Dioxide (SiO <sub>2</sub> )	17.5 %	16.0 - 18.0 %
Zirconium Oxide (ZrO <sub>2</sub> )	36.5 %	34.0 - 38.5 %
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> )	0.10 %	0.20 % max.
Titanium Dioxide (TiO <sub>2</sub> )	0.09 %	0.18 % max.
Sodium Oxide (Na <sub>2</sub> O)	0.20 %	0.25 % max.

#### Physical Characteristics

Specific Gravity:	3.94 g/cm <sup>3</sup>
α - Al <sub>2</sub> O <sub>3</sub> Phase:	4 %
Glassy Phase:	1750°

#### Available Sizing

3-5 mm, 1-3mm, 0.5-1 mm, 0-1 mm, 0-0.5 mm, 0-0.1 mm, 200/F, 325/F

Other sizes are available upon request.

#### Description:

GNP Graystar's Fused Zirconia Mullite is made of high purity raw materials in electric arc furnaces. The grain is characterized by high chemical purity, low thermal expansion, and high thermal shock resistance.

#### Applications:

GNP Graystar's Fused Zirconia Mullite is an excellent material for refractory applications such as glide gates, nozzles, and special refractory parts for the glass industry.

[info@GNPGraystar.com](mailto:info@GNPGraystar.com)

Rev. 02/2020

**Northern Office**  
37 John Glenn Dr.  
Amherst, NY 14228  
716.759.6600

[www.GNPGraystar.com](http://www.GNPGraystar.com)

**Southern Office**  
9 Simmonsville Rd.  
Bluffton, SC 29910  
843.815.5600