



TECHNICAL DATA SHEET

Semi-Friable Brown Aluminum Oxide

Typical Chemistry

	Microgrits
Aluminum Oxide (Al ₂ O ₃)	98.30 %
Titanium Oxide (TiO ₂)	1.58 %
Silicon Dioxide (SiO ₂)	0.04 %
Iron Oxide (Fe ₂ O ₃)	0.04 %
Calcium Oxide (CaO)	0.02 %

Physical Characteristics

Crystal Form	Alpha - Alumina
True Density	3.95 g/cm ³
Melting Point	2000°C
Color	Brown
Hardness	Knoop (50): 2100 Mohs: 9.0

Test Methods

Macrogrit Sizing:	ANSI B74.12 Table 2 ANSI B74.12 Table 3 Customer Specific Standards
Microgrit Sizing:	FEPA F Standard 42-2:2006 FEPA P Standard 43-2:2006 JIS R 6001-1987 Custom Sizes Available

Certifications Available

ANSI and FEPA
Agency & Mil-Specs (such as A-A-59316 & MIL-A-22262B)
Pratt & Whitney, Rolls Royce, Praxair, Stryker, etc.

Description:

GNP Graystar's Semi-Friable Brown Aluminum Oxide is fused in an electric arc furnace and produces a self-sharpening fused abrasive grain. **GNP Graystar's** semi-friable brown aluminum oxide is a low to medium bulk density product which is available in standard grades or can be custom graded for your application.

Applications:

GNP Graystar's Semi-Friable Brown Aluminum Oxide is used in all types of bonded and coated abrasive applications for ferrous and normal alloy steels.

info@GNPGraystar.com

Rev. 02/2020

Northern Office
37 John Glenn Dr.
Amherst, NY 14228
716.759.6600

www.GNPGraystar.com

Southern Office
9 Simmonsville Rd.
Bluffton, SC 29910
843.815.5600