



GNP Graystar

Specialty Materials

AN ISO 9001 CERTIFIED COMPANY




TECHNICAL DATA SHEET Boron Carbide Hot Press Powder

Typical Chemistry

Boron Carbide (B ₄ C)	95.15 %
Total Boron (B)	77.30 %
Free Boron (B)	0.56 %
Boron Oxide (B ₂ O ₃)	0.21 %
Compound Boron (B)	76.74 %
Total Carbon (C)	20.55 %
Free Carbon (C)	2.13 %
Iron Oxides (Fe ₂ O ₃)	0.09 %
Silicon (Si)	0.11 %

Typical Sizing

> 0%	> 3%	> 50%	> 75%	> 94%
14.26µm	9.076µm	4.294µm	3.018µm	1.516µm



Description:

GNP Graystar's Boron Carbide Hot Press Powder is specifically milled to 10 µm and finer with strict chemistry parameters for optimum performance.

- Available with or without a sintering aid.
- Granulated Powder available

Applications:

GNP Graystar's Boron Carbide Hot Press Powders are used for the production of various wear components, armor, blast nozzles, dressing sticks, etc.

info@GNPGraystar.com

Rev. 02/2020

Northern Office

37 John Glenn Dr.
Amherst, NY 14228
716.759.6600

www.GNPGraystar.com

Southern Office

9 Simmonsville Rd.
Bluffton, SC 29910
843.815.5600